

DOI: <http://dx.doi.org/10.21123/bsj.2017.14.4.0742>

Synthesis of Silver Nanoparticles from *Malva parviflora* Extract and Effect on Ecto-5'- Nucleotidase(5'-NT), ADA and AMPDA Enzymes in Sera of Patients with Arthrosclerosis

Ahlan M. Farhan¹

Rasha A. Jassim^{2*}

Nafeesa J. Kadhim³

Wesen Adel Mehdi⁴

Atheer Awad Mehde⁵

Received 12/12/2017, Accepted 11/3/2018, Published 3/6/2018



This work is licensed under a [Creative Commons Attribution 4.0 International License](https://creativecommons.org/licenses/by/4.0/).

Abstract:

The present research included synthesis of silver nanoparticle from (1×10^{-3} , 1×10^{-4} and 1×10^{-5}) M aqueous AgNO_3 solution through the extract of *M.parviflora* reducing agent. In the process of synthesizing silver nanoparticles we detected a rapid reduction of silver ions leading to the formation of stable crystalline silver nanoparticles in the solution. The characteristics of silver nanoparticles were studied by using UV-Visible absorption spectroscopy, and atomic force microscope (AFM) analysis. The AFM measurements showed that the average size of silver nanoparticles synthesized using (1×10^{-3} , 1×10^{-4} and 1×10^{-5}) M aqueous AgNO_3 solution through the extract of *M.parviflora* were 102 to 114nm. UV-Vis spectra of the aqueous medium containing silver nanoparticles showed a surface peak at 220nm and 445nm for (1×10^{-3} , 1×10^{-4} and 1×10^{-5}) M aqueous AgNO_3 solution through the extract of *M.parviflora*. The study of nanoparticles due to the possible application for the development of new technologies such as exhibited inhibitory effects on Ecto-5'-Nucleotidase (5'-NT), ADA and AMPDA enzymes in Sera of control and Patients with Arthrosclerosis. Further studies on other biological activities are required to exploit their full potential.

Keywords: *M.parviflora*, extract, Silver nitrate, Silver nanoparticles

Introduction:

Nanotechnology concerns with the development of empirical processes for the synthesis of nanoparticles of different sizes and shapes. That equipping an efficient monitoring abundant of the physical and chemical properties and their potential implementation in photoelectronic recording media sensing devices catalysis and medicine. To date, metallic nanoparticles are especially prepared from noble metals (ie, Ag, Pt, Au and Pd). Among the noble metals, (Ag) is the metal of choice in the field of biological system, living organisms and medicine (1).

Silver nanoparticle was used in wide range of applications such as, food industries, farming, weaves industries, water treatment as antimicrobial, cosmetics and salve(2). Silvery nanoparticles exhibit new or improved properties depending on

^{1, 2, 3, 4} Department of Chemistry, College of Science of Women, University of Baghdad, Baghdad, Iraq.

⁵Department of Pathologica Alanalyzes, College of Health and Medical Technology, Central Technical University, Baghdad, Iraq.

*Corresponding author: rashaaj-chem@csw.uobaghdad.edu.iq

forming, distribution and size. Different ways approaches using plant extract have been used for the synthesis of metal nanoparticles (3). Many technicality of synthesize silver nanoparticles like chemical reduction of silver ions in aquatic solutions with or without stability agents, thermic decomposition in organic solvents, alchemical shorthand while photoreduction in invert micelles, and radiation chemical reduction(4). *M.parviflora* L. belongs to the family Malvaceae that includes trees, shrubs and herbs. In Lesotho, dried powder or an infusion made from leaves and roots of *M.parviflora* use to clean wounds and sores. A hot scumble made from leaves is also used to treat wounds and tumefaction and is incorporated into a lotion to treat bruised and broken limbs. The leaves of *M.parviflora* use by the Xhosa people of South Africa for drawing swollen, inflamed purulent wounds. If ingested it is toxic such *M.parviflora* is remind to cases mortality in foraging livestock, such as sheep, horses and cattle. Sheep are the most often affected and develop clinical signs including arched back and labored breath. This toxicity that may be due to the presence of malvalic acid, an unsaturated fatty acid formerly referred to as halphen acid (5).

In this study, we have synthesized silver nanoparticles using *M.parviflora* extract. Then the study of nanoparticles on exhibited inhibitory effects on Ecto-5'- Nucleotidase (5'-NT), ADA and AMPDA enzymes in Sera of control and Patients with Arthrosclerosis.

Materials and Methods:

Synthesis of silver nanoparticles

In a typical reaction procedure, 5 mL of *M.parviflora* extract were add to 50mL of (1×10^{-3} , 1×10^{-4} and 1×10^{-5})M aqueous AgNO_3 solution at room temperature , the resulting solution become grey –black in color with (1×10^{-3} M) aqueous AgNO_3 solution, light yellow with (1×10^{-4} M) aqueous AgNO_3 solution and direct yellow with (1×10^{-5} M) aqueous AgNO_3 solution after 60 minutes ,indicating the formation of Ag NPs.

The Effect of AgNP on bacterial growth

To determine the growth curve in the presence of silver nanoparticles, *E. coli*, *Pseudomonas*, *Bacillus* and *staphylococcus* bacteria were grown in liquid LB medium. Fresh LB liquid medium were diluted in to optical density (OD600) 1×10^{-3} , 1×10^{-4} and 1×10^{-5} M. AgNP solution was added into the cell culture medium at different concentrations, and the culture was incubated at 37°C and 250 rpm. Growth rates and bacterial concentrations were determined by measuring OD at 600 nm at different time points (Fig.7).

Determination of Ag NPs on the sera adenosine aminohydrolase (ADA), AMP-aminohydrolase activities and Ecto-5'-nucleotidase activity.

The effect of Ag NPs on the levels of adenosine aminohydrolase (ADA), AMP-amino 11hydrolase and Ecto-5'-nucleotidase activities. In sera of patients with atherosclerosis and 50 healthy persons. This study was conducted on a group of 60 patients with atherosclerosis and 50 healthy persons to be used as control ranging between (40-75) years. These patients were hospitalized at Research Institute for educational laboratories in the city of Medicine of the Ministry of Health.

Results and Discussion

Analysis of Silver nanoparticles:

SEM analysis:

To determine the morphology of the synthesized silver nanoparticles the sample was analyzed with Scanning electron microscope (SEM). The scattered silver nanoparticles were dried in an oven for 1 hours to obtain a powdered form. Then, 2.5 mg of the sample was redispersed in ethanol and the sample was prepared in thin films on carbon coated

copper grid. Scanning electron microscopy provided further insight into the morphology and size details of the silver nano particles. Comparison of empirical results showed that the diameter of prepared nanoparticles in the solution was about 50 nm.




Figure 1. SEM image of the silver nanoparticle synthesized from *M.parviflora* leaf extracts.

UV-Vis Spectroscopy:

The reduction of the Ag^+ ions by the supernatant of the test plant extracts in the solutions and formation of silver nanoparticles was characterized by UV-visible spectroscopy monitored by sampling the aquatic component (2.0 mL) and gauge the UV-VIS spectrum of solutions. The UV-VIS spectroscopy of these specimens were measured on a UV-1800 Series spectrophotometer operated at a resolution of 1.0 nm.




Figure 2. UV–vis spectrum showing absorption of 10^{-3} M aqueous solution of silver nitrate with *M.parviflora* extract




Figure 3. AFM image of synthesized silver nanoparticles of (a) 10^{-3} M, (b) 10^{-4} M and (c) 10^{-5} M aqueous solution of silver nitrate with malvaparviflora extract.

The Effect of AgNP on bacterial growth

Chemical antimicrobial agents are progressively becoming resistant to a extensive spectrum of antibiotics. Another way to overcome the drug resistance of numerous bacteria is therefore instantly needed. Though, there are some limitations

in using Ag salts as antimicrobial agents, these may be due to the interfering effects of salts. Using silver in nano form can be removed these type of limitation, this may due to the increase of the surface area in nano case, the relate area between Ag(0) and that of the microorganism increases(12).




Figure 4. Antibacterial activity of AgNPs. Antibacterial activity of AgNP having different concentrations: (A) 1×10^{-3} M, (B) 1×10^{-4} M, and (C) 1×10^{-5} M, with (1) *E. coli*, (2) *Pseudomonas*, (3) *Bacillus* and (4) *staphylococcus* inoculated on nutrient agar plate. The 'Co' spot of the agar plate is for the blank test, having no AgNP.

The Effect of AgNPs on the sera adenosine aminohydrolase (ADA), AMP-aminohydrolase activities and Ecto-5'-nucleotidase activity.

In the previous study we referred to a highly significant elevated in the activities of Ecto-5'-nucleotidase(5'-NT), ADA and AMPDA enzymes U/L in patients with atherosclerosis compared to monitoring group. This is normally expressed in intravenous endothelial cells and in a broad range of impervious cells. Therefore, adenosine formative by extracellular nucleotide catabolism on endothelial cells and immune cells appears to be an important

endogenous modulator of arteriogenesis and key transcription factor involved in inflammatory responses (13). The inhibitory influence of the (Ag) NP on the activity of ADA, AMPDA and Ecto-5'-nucleotidase(5'-NT) were (38.68, 30.62 and 66.81%) respectively in patients group and (38.12, 30.95 and 66.92%) in control group when we used 50 μ L of AgNPs (Table 1 and 2). The percentage of inhibitory effect was showed highly when using 1×10^{-3} of AgNPs compared to 1×10^{-4} and 1×10^{-5} of AgNPs in both patients and control groups as shown in Table 1 and 2.

Table 1. The degree of inhibition of enzymes activities at (1×10^{-3} , 1×10^{-4} , 1×10^{-5}) M of AgNP, using 60 patients with atherosclerosis samples.

Enzymes	Patients group (n=60)	1×10^{-3} of AgNP			1×10^{-4} of AgNP			1×10^{-5} of AgNP		
		V(U/L)	% Inhib.	% Reco.	V(U/L)	% Inhib.	% Reco.	V(U/L)	% Inhib.	% Reco.
ADA (U/L) Mean \pm SD	46.23 \pm 14.65	28.35 \pm 13.02	38.68	61.32	39.74 \pm 16.89	14.03	85.96	42.35 \pm 12.01	8.40	91.60
AMPDA(U/L) Mean \pm SD	39.68 \pm 12.93	27.53 \pm 11.20	30.62	69.38	33.06 \pm 13.03	16.68	83.32	35.21 \pm 10.05	11.27	88.73
5'-NT (U/L) Mean \pm SD	52.21 \pm 16.33	17.33 \pm 10.97	66.81	33.19	38.65 \pm 12.08	25.97	74.03	42.35 \pm 10.01	18.89	81.11

2 the particle size was depend to increase the effect of percentage of inhibitory ,especially on Ecto-5'-nucleotidase(5'-NT) activity. Other consequence showed that smaller particles would greatly inhibiting the activity of ADA, AMPDA and Ecto-5'-nucleotidase(5'-NT) when it's used. This result needs to be further studied to determine the effect of particle size for activity of ADA, AMPDA and Ecto-5'-nucleotidase(5'-NT)in vivo ,in order to use the AgNPs in biomedical applications such as the treatment and follow up by adjustment the levels of

these enzymes of patients suffered from arthrosclerosis disorder.

Conclusion:

In this work, we have presented easy method for the preparation of AgNPs with well-defined size and shape. Silver nanoparticles with an average size of 102, 112 and 114nm were synthesized using aqueous solution of silver nitrate with *M.parviflora* extract.

Conflicts of Interest

The authors declare that they have no conflicts of interest.

References:

1. Sudha Lakshmi YG, Banu F, Sahadevan EA. Green Synthesis of Silver Nanoparticles from Cleome Viscosa: Synthesis and Antimicrobial Activity. IPCBEE, 2011; 5:334-337.
2. Gopinath K, Gowri Sh, Arumugam A. Phytosynthesis of silver nanoparticles using Pterocarpussantalinus leaf extract and their antibacterial properties, J. of Nano. In Chem., 2013; 3(68):1-7.
3. Awwad AM, Salem NM, Abdeen1 AO. Greensynthesis of silver nanoparticles using carob leaf extract and its antibacterial activity, International J. of Industrial. Chem., 2013; 4(29):1-6.
4. Forough M, Farhadi Kh. Biological and green synthesis of silver nanoparticles. Turkish J. Eng. Env., Sci. 2010; 34(4):281-287.
5. Farhan H, Rammal H, Hijazi A, Preliminary BB. Phytochemical Screening and Extraction of Polyphenol From Stems and Leaves of Alebanes Plant MalvaparvifloraL., International J. of Current Ph. Research, 2012; 4(1): 0975-706.
6. Giusti G, Galanti B, Mncini A. Serum guanase activity in iralhepatic and some other hepatic and extrahepatic disease. Enzymologia, 1970; 38:373-378.
7. Gromashevskaja L, Shkurova O, Magarlamov A. Adenosine deaminase and AMP-aminohydrolase activity of the blood serum in patients with jaundice. Vrachebnoe delo5: 1976; 137-43.
8. Wood R, Williams D. Colorimetric determination of serum 5-nucleotidase without deproteinization. Clin Chem, 1981; 27(4):64-465.
9. Forough M, Farhadi K. Biological and green synthesis of silver nanoparticles, Technical Note, Turkish J. Eng. Env. Sci. 2010; 34: 281–287.
10. Firdhouse MJ, Lalitha P, Sripathi ShK. Novel synthesis of silver nanoparticles using leaf ethanol extract of Pisoniagrandis (R. Br), Der Pharma Chemica, 2012; 4(6):2320-2326.
11. Bektash AA. A Study in Protection of Corrosion by Using Nanoparticles (TiO₂, SiO₂) for Some Metals and Alloys. MSc Thesis, University of Baghdad, Iraq, 2012; pp46.
12. Maiti S, Krishnan D, Barman G, Ghosh SK, Laha JK. Antimicrobial activities of silver nanoparticles synthesized from Lycopersi conesculentum extract. J. of Analytical Sci. and Tech., 2014; 5(40):1-7.
13. Mehdi W, Jasim N. Relationship between E3 SUMO-protein Ligase NSE2 (NSMCE2) with Ecto-5'-nucleotidase, ADA and AMPDA Enzymes in Patients with Atherosclerosis, Advances in Research 2015; 4(2): 79-86.

تحضير الفضة النانوية من مستخلص نبات الخباز والتأثير على Ecto-5'-نوكليو تيداز (5-NT)، ADA و AMPDA الانزيمات في مصول المرضى الذين يعانون من تصلب الشرايين

احلام محمد فرحان¹ رشا عبد جاسم² نفيسة جبار كاظم³ وسن عادل مهدي⁴ اثير عواد مهدي⁵

^{1,2,3,4} قسم الكيمياء، كلية العلوم للبنات، جامعة بغداد، بغداد، العراق.
⁵ قسم التحليلات المرضية، كليات التقنيات الصحية والطبية، الجامعة التقنية الوسطى، بغداد، العراق.

الخلاصة:

يتضمن البحث دراسة تحضير الدقائق النانوية من محلول نترات الفضة بتراكيز (1*10³ و 10⁴ و 10⁵) مولاري باستخدام مستخلص نبات الخباز كعامل مختزل من خلاله تحديد سرعة اختزال ايونات الفضة لتكون الدقائق البلورية الاكثر استقرارا للفضة بالمحلول. تم دراسة الخصائص الطيفية باستعمال طيف (UV-visible) ومجهر القوة الذرية (AFM) للدقائق النانوية المحضرة حيث تراوحت حجم الدقائق النانوية (102-114) نانوميتر بينما ظهر طيف (UV-visible) قمم تراوحت بين 220_445 نانوميتر على التوالي لتراكيز (1*10³ و 10⁴ و 10⁵) مولاري من محلول نترات الفضة من خلال مستخلص النبات، الدقائق النانوية تظهر تأثيرها كمثبط للانزيمات Ecto-5- Nucleotidase (5-NT), ADA and AMPDA المتواجدة في مصل الاشخاص الاصحاء والمرضى مع Arthrosclerosis.

الكلمات المفتاحية: مستخلص نبات الخباز، نترات الفضة، الفضة النانوية.